

Microanalysis Report


Prepared for: *Davit Setyobudi – Teknik Mesin UB*

Prepared by: *Laboratorium Sentral FMIPA UM*

3/11/2013



Logam Al



Element	Wt%	At%
<i>CK</i>	24.28	37.66
<i>OK</i>	21.97	25.58
<i>MgK</i>	01.63	01.25
<i>AlK</i>	49.93	34.47
<i>TiK</i>	00.46	00.30
<i>PK</i>	00.65	00.39
<i>FeK</i>	01.08	00.36
<i>Matrix</i>	Correction	ZAF

