


# Microanalysis Report


Prepared for: Miko Febritito K – Teknik Mesin UB

Prepared by: Laboratorium Sentral FMIPA UM




14/3/2013


## Logam Al 6061



Element	Wt%	At%
CK	25.59	39.33
OK	21.42	24.71
MgK	01.68	01.28
AlK	49.18	33.65
TiK	00.48	00.32
PK	00.66	00.39
FeK	00.99	00.33
Matrix	Correction	ZAF



Malang, 14 Mei 2013  
 a.n. Dekan FMIPA UM  
 Kepala Laboratorium Sentral,




*[Signature]*  
 Drs. Abdullloh Fuad, M.Si  
 NIP. 196302221988121002

# Microanalysis Report


Prepared for: Miko Febritito K – Teknik Mesin UB

Prepared by: Laboratorium Sentral FMIPA UM




14/3/2013

## Logam Al Titik 2



Element	WT%	AT%
CK	24.28	37.66
OK	21.97	25.58
MgK	01.63	01.25
AlK	49.93	34.47
TiK	00.46	00.30
PK	00.65	00.39
FeK	01.08	00.36
Matrix	Correction	ZAF



Malang, 14 Mei 2013  
 a.n. Dekan FMIPA UM  
 Kepala Laboratorium Sentral,




*[Signature]*  
 Drs. Abdulloh Fuad, M.Si  
 NIP. 196302221988121002



# Microanalysis Report


Prepared for: Miko Febritito K – Teknik Mesin UB

Prepared by: Laboratorium Sentral FMIPA UM





14/3/2013

## Logam Al 6061



Element	Wt%	At%
CK	26.38	40.32
OK	21.30	24.44
MgK	01.59	01.20
AlK	48.46	32.98
TiK	00.53	00.34
PK	00.56	00.33
FeK	01.20	00.39
Matrix	Correction	ZAF



Malang, 14 Mei 2013  
 a.n. Dekan FMIPA UM  
 Kepala Laboratorium Sentral,



*[Signature]*  
 Drs. Abdullloh Fuad, M.Si  
 NIP. 196302221988121002

