

Lampiran 4

Data Hasil Pengujian Permeabilitas Kaolin Putih

Fraksi Massa Kaolin Putih + <i>feldspar</i>	Volume air (ml) dalam waktu			
	0,5 jam	1 jam	1,5 jam	2 jam
45 + 25	3,60	6,30	7,20	7,20
40 + 30	2,70	5,40	6,30	6,30
35 + 35	3,60	7,20	9,00	9,00
30 + 40	6,30	9,90	11,70	12,60
25 + 45	4,50	8,10	9,90	9,90
20 + 50	5,40	9,00	9,90	10,80

Data Hasil Pengujian Permeabilitas Kaolin Coklat

Fraksi Massa Kaolin Coklat + <i>feldspar</i>	Volume air (ml) dalam waktu			
	0,5 jam	1 jam	1,5 jam	2 jam
45 + 25	2,70	5,40	7,20	8,10
40 + 30	2,70	3,60	5,40	6,30
35 + 35	3,60	9,00	10,80	12,60
30 + 40	9,00	14,40	17,10	18,90
25 + 45	5,40	10,80	12,60	13,50
20 + 50	3,60	9,90	12,60	14,40