



*PT. Justus Kimiaraya*

Head Office : WISMA JUSTUS  
Jl. Danau Sunter Utara No. 27 - 28, Blok O - 3,  
Jakarta 14350 - Indonesia  
Phone : (62-21) 6515188, 65306066, 65304880  
Fax : (62-21) 65305066  
E-mail : general\_jsr@justus.co.id ; Website : www.justus.co.id

## WOVEN ROVING

Specifications as follows:

ITEM	CWR 200	CWR 400	CWR 600	CWR 800
Area Weight	200 ± 10 g/m <sup>2</sup>	400 ± 10 g/m <sup>2</sup>	600 ± 10 g/m <sup>2</sup>	800 ± 10 g/m <sup>2</sup>
Moisture	1% Max	1% Max	1% Max	1% Max
Loss of Ignition	0.5 ± 0.2	0.5 ± 0.2	0.5 ± 0.2	0.5 ± 0.2
Type of glass	C-Glass	C-Glass	C-Glass	C-Glass
Density (Ends/cm)				
Warp	6.0 ± 0.6	4.0 ± 0.4	3.0 ± 0.3	1.8 ± 0.2
Weft	5.5 ± 0.6	4.0 ± 0.4	2.9 ± 0.3	1.8 ± 0.2
Breaking Strength (N)				
Warp	1000 ± 100	2000 ± 100	3500 ± 100	4000 ± 100
Weft	1000 ± 100	2000 ± 100	3100 ± 100	3800 ± 100
Oil Content	0.5 - 2.0 %	0.5 - 2.0 %	0.5 - 2.0 %	0.5 - 2.0 %

Woven roving (also called roving cloth) is the cloth plainly woven from the Direct Roving. It is used in processes such as Hand Lay-Ups, and in some of mechanical moldings. It can also be used with a chopped strand mat or fiberglass cloth for large size, high strength product that needs thicker laminates of more regular glass content. End products include boat, vehicle, pressure tank, houses, skis, etc.

Made in China

Des 2009