

Gliserol 2,0

Sampel Uji	M _o	M _t	Persen Penambahan Massa (%)
1	0,1387	0,2144	35,30%
2	0,1129	0,1721	34,39%
3	0,1136	0,1832	37,99%

Sorbitol 2,0

Sampel Uji	M _o	M _t	Persen Penambahan Massa (%)
1	0,1271	0,2207	42,41%
2	0,1245	0,2284	45,49%
3	0,1351	0,2558	47,18%

Tanpa Pemplastis

Sampel Uji	M _o	M _t	Persen Penambahan Massa (%)
1	0,0870	0,2476	64,86%
2	0,0822	0,2590	68,26%
3	0,0855	0,2583	70%