

Lampiran 1. Data Pengujian Kuat Tekan Mortar

Variasi Lerak	Benda Uji	Berat	Beban Maksimum	A	f _c	f _c rata-rata
		(kg)	(kg)	(cm ²)	(MPa)	(MPa)
0 cc	1	13,23	32300	17671,46	18,28	17,71
	2	12,19	31700	17671,46	17,94	
	3	11,21	29800	17671,46	16,90	
100 cc	1	9,62	20400	17671,46	11,54	10,79
	2	9,80	13500	17671,46	7,64	
	3	9,68	23300	17671,46	13,19	
200 cc	1	6,68	12700	17671,46	7,21	6,36
	2	5,80	7000	17671,46	3,96	
	3	6,09	13900	17671,46	7,90	
300 cc	1	5,37	5900	17671,46	3,39	3,06
	2	5,31	3500	17671,46	2,01	
	3	5,16	6600	17671,46	3,76	

